IN THE CLAIMS:

Please amend the claims as follows:

1. (Currently Amended) A high-pressure tank comprising:

a metallic tank body in which a cylindrical gas discharge section is protruded integrally from one end of a cylindrical middle section through a dome section; and

a cylindrical metallic reinforcing collar <u>fitted onto the cylindrical gas discharge</u> section of the tank body and <u>subsequently</u> engaged integrally on the exterior of the tank body between the cylindrical gas discharge section and the dome section by <u>shrink</u> fitting of the reinforcing collar onto the cylindrical gas discharge section of the tank body,

wherein the metallic tank body is formed by plastically deforming a hollow cylindrical blank of metal with rotation, and

the dome section in the vicinity of the boundary of the cylindrical gas discharge section and the cylindrical gas discharge section are increased in thickness as compared with the cylindrical middle section.

2. The high-pressure tank of Claim 1, wherein

the reinforcing collar is formed of a cylindrical part fitted onto the cylindrical gas discharge section of the tank body, and an extension extended radially outwardly from one end of the cylindrical part, the back of the extension being formed with an annular boss, and

the exterior of the tank body is formed with an annular fitting recess in the vicinity of the boundary between the dome section and the cylindrical gas discharge section so that the annular boss is fitted into the annular fitting recess with the reinforcing collar engaged on the exterior of the tank body between the cylindrical gas discharge section and the dome section.

- 3. The high-pressure tank of Claim 1 or 2, wherein the reinforcing collar is made of a steel alloy or a titanium alloy.
- 4. The high-pressure tank of Claim 1 or 2, wherein the tank body is made of an aluminum alloy.

5. (Withdrawn) A method for fabricating a high-pressure tank, comprising the steps of: plastically deforming a hollow cylindrical blank of metal with rotation to form a tank body in which a cylindrical gas discharge section is protruded integrally from one end of a cylindrical middle section through a dome section; and

then fitting a cylindrical metallic reinforcing collar onto the cylindrical gas discharge section of the tank body and engaging the reinforcing collar integrally on the exterior of the tank body between the cylindrical gas discharge section and the dome section by shrink fitting.

6. (Withdrawn) A method for fabricating a high-pressure tank, comprising the steps of:
plastically deforming a hollow cylindrical blank of metal with rotation to form a tank
body in which a cylindrical gas discharge section is protruded integrally from one end of a
cylindrical middle section through a dome section, followed by forming an annular fitting
recess circumferentially in the exterior of the tank body in the vicinity of the boundary
between the dome section and the cylindrical gas discharge section; and

then fitting a cylindrical metallic reinforcing collar having an annular boss onto the cylindrical gas discharge section of the tank body to fit the boss in the fitting recess of the dome section and engaging the reinforcing collar integrally on the exterior of the tank body between the cylindrical gas discharge section and the dome section by shrink fitting.